

Ryton® M2000 FP

polyphenylene sulfide

Ryton® M2000 FP, polyphenylene sulfide (PPS), is a nominal 50 micron powder grade, designed for applications including coating, sintering and

compression molding. Ryton® PPS exhibits excellent thermal stability and chemical resistance.

General

Material Status	• Limited Distribution	
Availability	• Asia Pacific • Europe	• Latin America • North America
Features	• Chemical Resistant • Good Thermal Stability	• Wear Resistant
Uses	• Additive Manufacturing (3D Printing) • Coating Applications	• Industrial Applications
RoHS Compliance	• RoHS Compliant	
Appearance	• Natural Color	
Forms	• Powder	
Processing Method	• Coating • Compression Molding	• Sintering

Physical

	Typical Value	Unit	Test method
Density / Specific Gravity	1.34		ASTM D792
Melt Mass-Flow Rate (MFR) ¹ (316°C/5.0 kg)	100	g/10 min	ASTM D1238
Water Absorption (24 hr, 23°C)	0.050	%	ASTM D570
Ash Content	0.10	wt%	ISO 3451-1
Average Particle Size - D50	50	µm	Internal Method
Volatiles (150°C)	< 0.30	wt%	

Thermal

	Typical Value	Unit	Test method
Deflection Temperature Under Load 1.8 MPa, Unannealed	95.0	°C	ASTM D648
Glass Transition Temperature	90.0	°C	ISO 11357-2
Vicat Softening Temperature	> 180	°C	ISO 306
Melting Temperature	280	°C	ISO 11357-3
CLTE - Flow (-50 to 50°C)	5.0E-5	cm/cm/°C	ASTM E831

Electrical

	Typical Value	Unit	Test method
Volume Resistivity	1.0E+16	ohms·cm	ASTM D257
Dielectric Strength			ASTM D149
1.50mm thick specimen	24	kV/mm	
100µm thick film	90	kV/mm	
Dielectric Constant (25°C, 1 MHz)	3.20		ASTM D150
Dissipation Factor (25°C, 1 MHz)	2.0E-3		ASTM D150

Ryton® M2000 FP

polyphenylene sulfide

Notes

Typical properties: these are not to be construed as specifications.

¹ Procedure B

www.syensqo.com

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Syensqo nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Syensqo's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Syensqo's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Syensqo or their respective owners.

© 2024 2023 Syensqo. All rights reserved.

